

Brilliant Resilient Hair Gel All Day Hold and Shine

All day hold and shine for a look that's brilliant and resilient.

Products Used Acudyne™ DHR Hair Fixative Resin, Aculyn™ 88 Rheology Modifier, Neolone™ PE Preservative

Ingredients:

Ph	Trade Name	%Wt.	CTFA / INCI Name	Supplier
1	Water, deionized	87.10	Water	N/A
	Acudyne™ DHR	2.20	Acrylates/Hydroxyesters Acrylates Copolymer	Rohm and Haas
	Aculyn™ 88	5.00	Acrylates/Steareth-20 Methacrylate Crosspolymer	Rohm and Haas
2	AMP-95™	0.90	Aminomethyl Propanol	Angus
3	Bergamont Bliss	0.30	Fragrance	Custom Essence
	Chemonic™ LI-63	2.00	PEG-30 Glyceryl Cocoate	Chemron
	Ritabate™ 20	1.50	Polysorbate 20	Rita
4	Aloe Vera Extract	0.25	Aloe Barbadensis Leaf Extract	Bell Flavor & Fragrance
	Green Tea Extract	0.25	Camellia Oleifera Seed Extract	Bell Flavor & Fragrance
	Neolone™ PE	0.50	Phenoxyethanol (and) Methylisothiazolinone	Rohm and Haas

Processing Instructions:

1. Combine phase 1, one ingredient at a time while stirring.
2. Add phase 2 to phase 1, and continue stirring until a clear solution is formed.
3. Combine phase 3, while stirring slowly until clear and homogeneous.
4. Add phase 3 to mixture from step 2, mix well.
5. Add phase 4 to step 4 mixture, stir until homogeneous.

Product Characteristics:

Parameter	Range	Method
pH (as is)	7.3-7.6	pH Meter
Viscosity	18,000-22,000 cps	Brookfield RV, Spindle# 6, 20 rpm
Appearance	Clear	Visual

Date of Last Revision:
Oct. 5, 2005

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control, Rohm and Haas Company makes no warranties either expressed or implied as to the accuracy

or appropriateness of this data. Rohm and Haas Company expressly disclaims any implied warranty of fitness for a particular use. We recommend that the prospective users determine for themselves the suitability of Rohm and Haas materials and suggestions for any use prior to their adoption.



For Questions or Comments, please email CISPCFormulations@RohmHaas.com